

## > PROTECTIVE WATERPROOF COATING PRODUCTS



PYE Products..... *easy to use*



## PYE PRUFLOAT 127

*Flexible Waterproofing Slurry*

### DESCRIPTION

**PYE PRUFLOAT 127** is used for waterproofing or damp proofing concrete or mortar surfaces. The area to be treated can be either existing or newly created surfaces. **PYE PRUFLOAT 127** should not be used on painted surfaces or surfaces that have been treated with water repellent.

### SUITABLE FOR

- Bathroom floor & walls
- Planter boxes
- Balconies & terrace
- RC gutters

### ADVANTAGES

- Good adhesion
- Hard & slightly flexible
- Waterproofs and damp proofs masonry surfaces

### DIRECTIONS FOR USE

#### *Surface preparation*

Surfaces must be clean and free from standing water, grease, dust or any loose materials in order to achieve a good bonding. Avoid cracks and fillet edge, shall repaired to ensure that the surface is sound, even and clean. Dampen the surface if it is dry. Remove any excess water.

#### *Mixing*

Add 1 portion of Part B to 4 portions of Part A. Mixing can be done manually or by the use of an electric mixer to form a paste - like consistency to be brushed onto the concrete surface. Allow the liquid soak into the powder at least 5 minutes before remixing again. Use within 30 minutes.

#### *Application*

To be applied horizontally for the first coat and vertically for the second or vice versa. Apply the first coat when the surface is still damp. Leave to cure for approximately 4 to 8 hours at room temperature before applying second coat. For best results it is recommended that the second coat be applied after 24 hours (usually for floor applications). **PYE PRUFLOAT 127** can be applied using a trowel or a hard paint brush.

**Product code: PRPC**

- For waterproofing bathrooms, terraces and balconies: 1kg/m<sup>2</sup> per coat, with a minimum of 2 coats are required.
- For waterproofing coating up to 1m water head: 1.5kg/m<sup>2</sup>, with a minimum of 2 coats are required.
- For waterproofing coating more than 1m water head: 2kg/m<sup>2</sup>, with a minimum of 2 coats are required.

Note: **PYE PRUFLOAT 127** must be applied in a minimum of 2 coats and must not be applied more than 2kg/m<sup>2</sup> in a single layer.

### TECHNICAL & PHYSICAL DATA

Colour	Natural cement
Form	Part A: Powder / Part B: Liquid
Solids	Cement and high grade silica.
Admixture	High strength acrylic polymers.
Pot life	Approx. 2 hours
Thickness	2 - 3mm
Coverage	1kg/mm/m <sup>2</sup>
Health & Safety	Non-hazardous Non-flammable Non-toxic
Storage	Store in a dry cool place.
Shelf life	6 months when unopened.
Cleaning	Clean tools with water. If harden remove mechanically.

### PACKING

25kg/ set

Further information and advice are freely available from:

**PYE PRODUCTS (M) SDN. BHD.** (Co. No. 206933-D)

Lot 4993, 5½ Mile Jalan Meru, 41050 Klang, Selangor Darul Ehsan, Malaysia.

Tel : 603-3392 8104, 3392 8112 Fax : 603-3392 8097

E-mail : enquiry@pyeproducts.com Website : www.pyeproducts.com



All information contained within this brochure is only intended to give a fair description of the products and their capabilities under specific test conditions. However, it does not constitute an offer of warranty by the manufacturer nor a guarantee of its accuracy or completeness in describing the performance or suitability of the various products.