

> PROTECTIVE WATERPROOF COATING PRODUCTS



PYE Products..... easy to use



PYE PRUFÇOAT
Flexible Waterproofing Slurry

DESCRIPTION

PYE PRUFÇOAT is used for waterproofing or damp proofing concrete or mortar surfaces. The area to be treated can be either existing or newly created surfaces. **PYE PRUFÇOAT** should not be used on painted surfaces or surfaces that have been treated with water repellent.

SUITABLE FOR

- Bathroom floor & walls
- Planter boxes
- Balconies & terrace
- RC gutters

ADVANTAGES

- Good adhesion
- Hard & slightly flexible
- Waterproofs and damp proofs masonry surfaces

DIRECTIONS FOR USE

Surface preparation

Surfaces must be clean and free from standing water, grease, dust or any loose materials in order to achieve a good bonding. Avoid cracks and fillet edge, shall repaired to ensure that the surface is sound, even and clean. Dampen the surface if it is dry. Remove any excess water.

Mixing

Add 1 portion of Part B to 4 portions of Part A. Mixing can be done manually or by the use of an electric mixer to form a paste - like consistency to be brushed onto the concrete surface. Allow the liquid soak into the powder at least 5 minutes before remixing again. Use within 30 minutes.

Application

To be applied horizontally for the first coat and vertically for the second or vice versa. Apply the first coat when the surface is still damp. Leave to cure for approximately 4 to 8 hours at room temperature before applying second coat. For best results it is recommended that the second coat be applied after 24 hours (usually for floor applications).

PYE PRUFÇOAT can be applied using a trowel or a hard paint brush.

Product code: **PRPR**

- For waterproofing bathrooms, terraces and balconies: 1kg/m² per coat, with a minimum of 2 coats are required.
- For waterproofing coating up to 1m water head: 1.5kg/m², with a minimum of 2 coats are required.
- For waterproofing coating more than 1m water head: 2kg/m², with a minimum of 2 coats are required.

Note: **PYE PRUFÇOAT** must be applied in a minimum of 2 coats and must not be applied more than 2kg/m² in a single layer.

TECHNICAL & PHYSICAL DATA

Colour	Natural cement
Form	Part A: Powder / Part B: Liquid
Solids	Cement and high grade silica.
Admixture	High strength acrylic polymers.
Pot life	Approx. 2 hours
Thickness	2 - 3mm
Coverage	1kg/mm/m ²
Health & Safety	Non-hazardous Non-flammable Non-toxic
Storage	Store in a dry cool place.
Shelf life	6 months when unopened.
Cleaning	Clean tools with water. If harden remove mechanically.

PACKING

22.5kg/ set

Further information and advice are freely available from:

PYE PRODUCTS (M) SDN. BHD. (Co. No. 206933-D)

Lot 4993, 5½ Mile Jalan Meru, 41050 Klang, Selangor Darul Ehsan, Malaysia.

Tel : 603-3392 8104, 3392 8112 Fax : 603-3392 8097

E-mail : enquiry@pyeproducts.com Website : www.pyeproducts.com



All information contained within this brochure is only intended to give a fair description of the products and their capabilities under specific test conditions. However, it does not constitute an offer of warranty by the manufacturer nor a guarantee of its accuracy or completeness in describing the performance or suitability of the various products.